

AFT450W

45 MIL PREMIUM ACRYLIC FOAM TAPE

DESCRIPTION

Double coated with an aggressive pressure-sensitive acrylic formulation, this acrylic foam tape is engineered to bond to almost any surface. Excellent resistance to solvents and temperature variances. Conforms well to curves, moves and flexes as needed on applications requiring contortion and bending characteristics.

PRODUCT APPLICATION

General purpose acrylic foam tape intended for use in mounting and bonding with appliances, electronic devices, signage, graphics, side molding, emblems, and weather stripping. Not intended for assembly of trailers and pull-behinds unless in conjunction with mechanical fasteners. Also not intended for use in permanent assembly or attachment of cladding and curtain wall architectural panels.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 11/17

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	Acrylic Foam
Adhesive	Acrylic
Adhesion to Steel (oz/in of width)	
Room Temp x 20 minutes	179 (49.0 N/25mm)
Room Temp x 24 hours	224 (61.3 N/25mm)
80°C (176°F) x 250 hours	170 (46.5 N/25mm)
-20°C (-4°F) x 250 hours	152 (41.6 N/25mm)
Static Shear Adhesion to Steel (7 days)	
3.22cm (1.25") x 1500g @23°C	Pass
3.22cm (1.25") x 500g @93°C	Pass
Dynamic Shear Adhesion to Steel (oz/in width) (10mm x 10mm @ 200mm / minute removal speed)	
@ Room Temp x 20 mins	868 (237 N/25mm)
@ Room Temp x 24 hours	868 (237 N/25mm)
@ Room Temp x 48 hours	895 (245 N/25mm)
@ Room Temp/100% RH x 250 hrs	877 (240 N/25mm)
@ 80°C (176°F) x 250 hours	913 (250 N/25mm)
@ -20°C (-4°F) x 250 hours	806 (220 N/25mm)
Temperature Resistance	
Short Term	4 hours
25mm x 25mm x 100g +150°C (302°F) Stainless Steel	
Long Term	17 hours
25mm x 25mm x 250g +93°C (200°F) Stainless Steel	
Total Thickness without Liner (mils)	45 (1.14 mm)
Liner Type/Thickness (mils)	PE - Red 4.8 (0.12mm)
Color	White

