

Stretch Film

Orbit Air B (High Performance Pre-Stretched Hand Wrap)

INTERTAPE POLYMER GROUP®
TECHNICAL DATA SHEET

Test	Values (listed by film thickness)			
	Reference Methods	24 gauge 6.1 micron 0.24 mil	30 gauge 7.6 micron 0.30 mi	36 gauge 9.1 micron 0.36 mi
Ultimate Tensile MD (psi)	ASTM D882	11,700	13,000	14,000
Ultimate Tensile TD (psi)	ASTM D882	2,645	3200	3600
Elongation MD (%)	ASTM D882	128	162	180
Elongation TD (%)	ASTM D882	617	650	675
Tear Resistance MD (grams and g/mil)	ASTM D1922	54 grams	66 grams	72 grams
		225 g/mil	219 g/mil	205 g/mil
Tear Resistance TD (grams and g/mil)	ASTM D1922	188 grams	232 grams	270 grams
		783 g/mil	773 g/mil	760 g/mil

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
 Customer Service: 888.898.7834
www.itape.com | info@itape.com

EFFECTIVE: 4/13/20

